

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 127 673 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
29.08.2001 Bulletin 2001/35

(51) Int Cl.7: **B29C 45/14**

(21) Application number: **00610024.2**

(22) Date of filing: **23.02.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• Nilsson, Gert
275 38 Sjöbo (SE)
• Persson, Michael
S-261 93 Landskrona (SE)

(71) Applicant: **TELEFONAKTIEBOLAGET LM
ERICSSON**
126 25 Stockholm (SE)

(74) Representative: **Boesen, Johnny Peder et al
Hofman-Bang A/S
Hans Bekkevolds Allé 7
2900 Hellerup (DK)**

(54) **A method of manufacturing a shell element provided with an opening in an angled part and a shell element manufactured by said method**

(57) A method of manufacturing a shell element (13) for an electronic device, said shell element (13) having a front (5) and at least one part that is angled in relation to said front (5). The shell element (13) further comprises a formed sheet (6) that constitutes at least a part of the outer surface of said front (5) and at least a part of said part that is angled in relation to the front of the shell element (13). The method comprises the steps of first forming a sheet (1) to a desired shape including a part

that is angled in relation to a front part (5) and then injection moulding a plastics material on the back of the formed sheet (6). At least one opening (7) is provided in the angled part of the formed sheet (6) before the plastics material is injection moulded on the back of the formed sheet (6) and the at least one opening (7) is left open during the injection moulding of a plastics material on the back of the formed sheet (6).

A shell element manufactured by this method is also disclosed.




Fig. 2a

Best Available Copy

EP 1 127 673 A1




Fig. 2b

Description

[0001] The invention relates to a method of manufacturing a shell element for an electronic device, said shell element having a front and at least one part that is angled in relation to said front, said shell element further comprising a formed sheet that constitutes at least a part of the outer surface of said front and at least a part of said part that is angled in relation to the front of the shell element, said method comprising the steps of:

- forming a sheet to a desired shape including a part that is angled in relation to a front part,
- injection moulding a plastics material on the back of the formed sheet.

[0002] The invention further relates to a shell element manufactured by this method.

[0003] The term electronic device includes portable radio communication equipment which includes all equipment such as mobile telephones, pagers, communicators, i.e. electronic organizers, smartphones or the like. Another example of an electronic device is a Personal Digital Assistant (PDA).

[0004] In order to produce electronic equipment such as mobile phones with varying outer appearances, a number of different techniques have been developed. One of these techniques is the one described above in which a sheet of e.g. PC (polycarbonate) is provided with a decoration in terms of a print. The sheet is then formed into a desired shape by first heating the sheet, e.g. in an infra-red oven, and then use any conventionally known technique to form the heated sheet, e.g. by high pressure forming, hydro forming or vacuum forming. The heated sheet may also be positioned in a press mould with mould parts that form the sheet into the desired shape.

[0005] When the sheet is cooled, it is removed from the press mould or male form part. In relation to the present invention, the formed sheet is provided with at least one part - preferably a circumferential flange - that is angled in relation to the front of the formed sheet.

[0006] Usually, the edges of the formed sheet are trimmed and openings for e.g. keys and a display are provided in the front of the formed sheet. The openings may be made by punching or cutting.

[0007] The formed sheet is then positioned in an injection mould in which one mould part has an inner shape that is complementary to the outer shape of the formed sheet and of the finished shell element. The mould part is provided with protrusions that extend into the openings of the formed sheet. The protrusions of the mould part abut the other mould part when the injection mould is closed.

[0008] A plastics material, such as PC or ABS, is injected into the closed injection mould onto the back of the formed sheet. Due to the above-mentioned protrusions

the finished shell element is provided with openings corresponding to the openings in the formed sheet.

[0009] When the plastics material is cooled, the finished shell element is removed from the injection mould. The shell element needs no further trimming.

[0010] By using the above-described method, varying outer appearances of e.g. mobile phones may be accomplished by varying only the printed decoration on the sheet, i.e. the method of manufacturing remains unchanged. This technique has therefore been found to be economically beneficial if it is desired to vary the outer appearances of a shell element for electronic devices.

[0011] JP patent abstract No. 59-152,834 discloses a method of manufacturing a plastics injection moulded item with openings and an injection mould therefore. The injection mould is provided with stamping pins that punch the openings in a preformed and decorated sheet when the injection mould is closed. The plastics material is then injection moulded directly on the back of the preformed sheet to form a finished shell element.

[0012] According to the prior art, shell elements of the type described above are manufactured with openings in the front part only. If a component is to be mounted in a part of the shell element that is angled in relation to the front part, this area is provided with a notch extending from the edge, and the component is mounted in the notch. However, this way of mounting a component does not fasten the component satisfactorily to the shell element since, at the one side, the component is not supported by the shell element.

[0013] A bore may be provided in the angled area for mounting a component securely. This, however, requires an additional working procedure which further results in more waste from the removed material.

[0014] It is an object of the invention to provide a method of manufacturing a shell element of the above-mentioned type in which it is possible to mount a component directly in an opening in an angled area in relation to the front part of the shell element, which method overcomes the above-mentioned problems.

[0015] This object is achieved by providing at least one opening in the angled part of the formed sheet mentioned in the opening paragraph, said opening being provided before the plastics material is injection moulded on the back of the formed sheet and leaving the at least one opening open during the injection moulding of a plastics material on the back of the formed sheet.

[0016] Thereby the finished shell element is manufactured with an opening in an angled part without need for any further trimming.

[0017] The opening in the angled part of the formed sheet is preferably punched or cut out. The punching or cutting of the opening in the angled part may be performed in the same tool and in the same working procedure in which the openings in the front of the formed sheet is punched or cut, or it may be provided in a separate tool.

[0018] The edges of the formed sheet are preferably

trimmed and openings in the front part of the formed sheet, if any, are preferably provided before the plastics material is injection moulded on the back of the formed sheet. Thereby no further trimming of the finished shell element after injection moulding is necessary.

[0019] The injection mould may be provided with at least one raised portion that extends into at least one opening of the formed sheet when the formed sheet is positioned in the injection mould, or it may be provided with at least one displaceable core member that is displaced into at least one opening of the formed sheet when the formed sheet is positioned in the injection mould.

[0020] If the injection mould is provided with raised portions, the injection mould can be made relatively simple. This structure requires, however, that the formed sheet as well as the finished shell element is sufficiently flexible in order to flex into and out of the injection mould part that has these raised portions. A more complex structure of the injection mould is achieved if it is provided with displaceable cores. However, if the material used is relatively unflexible, this may be a preferred injection mould structure since the formed sheet can be positioned directly in the injection mould without flexing, and the finished shell element can be removed from the injection mould without flexing.

[0021] The formed sheet may preferably cover the entire front of the shell element while the angled part comprises a circumferential flange that extends from the front of the shell element. Thereby the outlook of the shell element is determined solely by the appearance of the formed sheet. The plastics material that is injection moulded onto the back of the formed sheet can therefore be of any kind that fulfils the physical requirements to the material regardless of colour and appearance.

[0022] In a preferred embodiment the sheet is a plastics material, such as polycarbonate (PC), and the material that is injection moulded on the back of the formed sheet is also a plastics material, such as PC or ABS. Such plastics materials can be easily formed to the desired shape and are very suitable for injection moulding and calls for good chemical bonding between the formed sheet and the backing.

[0023] The electronic device, which the shell element is intended for, is preferably a mobile radio station, such as a mobile telephone.

[0024] It shall be emphasised that the term "comprise/comprising" when used in this specification is taken to specify the presence of stated features, integers, steps or components but does not preclude the presence or addition of one or more other features, integers, steps or components or groups thereof.

[0025] The invention will be described in detail in the following with reference to the drawings in which

Fig. 1 stepwise shows the manufacturing of a shell element according to the invention,

Figs. 2a and 2b each shows a cross-section of an injection mould in a first embodiment for use in the method of manufacturing according to the invention, and

Fig. 3 shows a cross-section of an injection mould in a second embodiment for use in the method of manufacturing according to the invention.

[0026] Fig. 1 shows the manufacturing process for a shell element having openings in side parts that are angled in relation to the front of the shell element.

[0027] The starting material is a sheet 1 of a plastics material, such as polycarbonate (PC). The sheet 1 is provided with a print 2 which may comprise more than one colour or pattern as shown. The print may be provided at one or either side of the sheet 1 or it may be provided between two layers of a laminated sheet 1.

[0028] The sheet 1 is heated, e.g. in an infra-red oven 3 as schematically illustrated, and is then formed into a desired shape by any known process, such as high pressure forming, vacuum forming, hydro forming or in a press tool. These forming processes are well-known in the art and are not shown in details. The preferred process is the high pressure forming process in which the sheet is positioned over a male form and pressurized air is applied to the outer side of the heated sheet.

[0029] The edge of the sheet 1 is trimmed by cutting, and openings 4 are punched or cut in the front 5 of the formed sheet 6. Openings 7 are also punched or cut in the flange 8 extending from the front 5 of the formed sheet 6. The flange 8 is angled in relation to the front 5 of the formed sheet 6. The angulation may in a preferred embodiment be about 90° as shown, i.e. the flange 8 extends in a substantially right angle in relation to the front 5 of the formed sheet 6.

[0030] At this point in the manufacturing process the formed and trimmed sheet 6 has achieved the desired shape and no further trimming is needed.

[0031] The formed sheet 6 is positioned in a lower mould part 9a of an injection mould. This lower mould part 9a is provided with a recess 10 having a shape that is complementary to the shape of the formed sheet 6, i.e. the formed sheet 6 fits snugly into the recess 10. The recess 10 is provided with raised portions 11, 12 that fit into the openings 4, 7 provided in the formed sheet 6. The raised portions 11, 12 are abutted by the upper mould part 9b when the mould is closed, thereby forming cores for moulding openings in the finished shell element 13.

[0032] The upper mould part 9b is provided with a sprue cup 14 through which the plastics material, such as PC or ABS, is injected. The injected plastics material spreads throughout the injection mould, forming a backing for the formed sheet 6 by adhering to the back of it and creating openings defined by the raised portions 11, 12 of the injection mould.

[0033] When cooled, the finished shell element 13 is

ejected from the injection mould and is ready to be furnished with components extending through the openings 4, 7, i.e. no further trimming is necessary.

[0034] Figs. 2a and 2b show schematically a cross-section through an opened and a closed injection mould corresponding to the injection mould disclosed in Fig. 1.

[0035] The injection mould comprises a lower injection mould part 9a and an upper injection mould part 9b. The lower injection mould part 9a is provided with raised portions 11, 12 that protrude from the inner sidewall into the recess 10. A formed sheet 6 is positioned in the recess 10, ready for injection moulding of a plastics material on the back of it. The formed sheet 6 is relatively thin and flexible and it can usually be pressed readily into the shown position having the raised portions 11, 12 extending through the openings 4, 7 of the formed sheet 6.

[0036] Since the raised portions 11 and 12 extend in different directions, the formed sheet 6 is securely retained in the recess when it is positioned as shown. Thus, provision of openings in the angled part or flange 8 of the formed sheet 6 calls for good retaining of the formed sheet 6 in the injection mould recess 10.

[0037] After the formed sheet 6 is positioned in the recess 10, the injection mould is closed as shown in Fig. 2b. The upper injection mould part 9b is provided with a male part 15 that fits into the recess 10, abutting on the raised portions 11, 12. When a plastics material is injected through the sprue cup 14, it spreads throughout the injection mould, adhering to the back of the formed sheet 6 and creating openings defined by the raised portions 11, 12 abutting the male part 15.

[0038] When the plastics material is cooled, the injection mould is opened and the finished shell element 13 is ejected. In order to eject the finished shell element 13, the flange 8 is pressed inwards to release the opening 7 from the raised portion 12.

[0039] Fig. 3 shows a cross-section of an injection mould in a second embodiment for use in the method of manufacturing according to the invention.

[0040] This injection mould corresponds to the injection mould shown in Figs. 2a and 2b except that the raised portions 12 have been replaced by displaceable core members 22. This means that, when the core members 22 are retracted, the finished shell element 13 can be ejected from the injection mould without deforming the flange 8, which is otherwise the case when the raised portions 12 are fixed as shown in Figs. 2a and 2b. An injection mould having displaceable core members 22 may also advantageously be applied if the formed sheet 6 is made of a relatively unflexible material that cannot be deformed so as to snap over any fixed protrusions like the raised portions 12 shown in Figs. 2a and 2b.

[0041] A preferred embodiment for a shell element according to the invention has been described above with reference to the drawings. It should be realized, however, that the shell element may have other forms than the

one shown. For instance, the formed sheet could constitute only a part of the surface of the front of the shell element, whereas the injection moulded plastics material constitutes a backing for the formed sheet as well as a part of the outer surface of the front of the shell element. According to the invention, however, at least a part of the formed sheet is angled in relation to the front of the shell element, said angled part being provided with at least one opening.

Claims

1. A method of manufacturing a shell element (13) for an electronic device, said shell element (13) having a front (5) and at least one part that is angled in relation to said front (5), said shell element (13) further comprising a formed sheet (6) that constitutes at least a part of the outer surface of said front (5) and at least a part of said part that is angled in relation to the front of the shell element (13), said method comprising the steps of:

- forming a sheet (1) to a desired shape including a part that is angled in relation to a front part (5),
- injection moulding a plastics material on the back of the formed sheet (6),

characterised in

- providing at least one opening (7) in the angled part of the formed sheet (6) before the plastics material is injection moulded on the back of the formed sheet (6) and leaving the at least one opening (7) open during the injection moulding of a plastics material on the back of the formed sheet (6).

2. A method according to claim 1, **characterised in that** the opening in the angled part of the formed sheet (6) is punched out.

3. A method according to claim 1, **characterised in that** the opening in the angled part of the formed sheet (6) is cut out.

4. A method according to any one of claims 1-3, **characterised in** trimming the edges of the formed sheet (6) before the plastics material is injection moulded on the back of the formed sheet (6).

5. A method according to any one of claims 1-4, **characterised in** providing at least one opening (4) in the front part of the formed sheet (6) before the plastics material is injection moulded on the back of the formed sheet (6).

6. A method according to any one of claims 1-5, **characterised in that** the injection mould (9a, 9b) is provided with at least one raised portion (11, 12) that extends into at least one opening (4, 7) of the formed sheet (6) when the formed sheet (6) is positioned in the injection mould (9a, 9b) for injection moulding a plastics material on the back of the formed sheet (6). 5
7. A method according to any one of claims 1-6, **characterised in that** the injection mould (9a, 9b) is provided with at least one displaceable core member (22) that is displaced into at least one opening (7) of the formed sheet (6) when the formed sheet (6) is positioned in the injection mould (9a, 9b) for injection moulding a plastics material on the back of the formed sheet (6). 10
8. A method according to any one of claims 1-7, **characterised in that** the formed sheet (6) covers the entire front (5) of the shell element (13) and that the angled part comprises a circumferential flange (8) that extends from the front (5) of the shell element (13). 15
9. A method according to any one of claims 1-8, **characterised in that** the sheet (1) is a plastics material, such as polycarbonate (PC). 20
10. A method according to any one of claims 1-9, **characterised in that** the material that is injection moulded on the back of the formed sheet (6) is a plastics material, such as PC or ABS. 25
11. A method according to any one of claims 1-10, **characterised in that** the electronic device is a mobile radio station, such as a mobile telephone. 30
12. A shell element (13) for an electronic device, said shell element (13) having a front (5) and at least one part that is angled in relation to said front (5), said shell element (13) comprising 35
- a formed sheet (6) that constitutes at least a part of an outer surface of said front (5) and at least a part of said part that is angled in relation to the front (5) of the shell element (13), 40
 - a backing that is injection moulded on the back of the formed sheet (6), 45
- characterised in that** at least one opening (7) is provided in the part of the shell element (13) that is angled in relation to the front (5) of the shell element (13), said opening (7) being provided by injection moulding around a core (12, 22) that during the injection moulding extends through an opening (7) provided in the formed sheet (6). 50 55
13. A shell element according to claim 12, **characterised in that** the formed sheet (6) covers the entire front (5) of the shell element (13) and that the angled part comprises a circumferential flange (8) that extends from the front (5) of the shell element (13). 5
14. A shell element according to claims 12 or 13, **characterised in that** at least one opening (4) is provided in the front (5) of the shell element (13). 10
15. A shell element according to any one of claims 12-14, **characterised in that** the sheet (1) is a plastics material, such as polycarbonate (PC). 15
16. A shell element according to any one of claims 12-15, **characterised in that** the material that is injection moulded on the back of the formed sheet (6) is a plastics material, such as PC or ABS. 20
17. A shell element according to any one of claims 12-16, **characterised in that** the electronic device is a mobile radio station, such as a mobile telephone. 25




Fig. 1




Fig. 2a




Fig. 2b




Fig. 3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 61 0024

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 03, 30 March 2000 (2000-03-30) -& JP 11 348072 A (PFU LTD), 21 December 1999 (1999-12-21) * abstract *	1,6-8, 12,13	B29C45/14
A	PATENT ABSTRACTS OF JAPAN vol. 10, no. 77 (M-464), 26 March 1986 (1986-03-26) -& JP 60 219021 A (TOYOTA JIDOSHA KK), 1 November 1985 (1985-11-01) * abstract *	4	
A	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 04, 31 May 1995 (1995-05-31) -& JP 07 007284 A (KOMATSU LTD), 10 January 1995 (1995-01-10) * abstract *	5,7,8, 13,14	
A	WO 81 00654 A (MOTOROLA INC) 5 March 1981 (1981-03-05) * the whole document *	1,5,11, 12,14,17	TECHNICAL FIELDS SEARCHED (Int.Cl.7) B29C H04M
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 5 July 2000	Examiner Bollen, J
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 61 0024

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

05-07-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 11348072 A	21-12-1999	NONE	
JP 60219021 A	01-11-1985	NONE	
JP 07007284 A	10-01-1995	NONE	
WO 8100654 A	05-03-1981	EP 0034624 A	02-09-1981

EPO FORM P059

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.